

Orientational Ordering in Sequence-Disordered Liquid Crystalline Polymers

Lorin Gutman and Eugene Shakhnovich

Department of Chemistry and Chemical Biology, Harvard University, Cambridge, MA 02138

Phase separation of sequence-disordered liquid crystalline polymers, a promising class of technological and biological relevance, is studied by field theory, and thermodynamic mechanisms responsible for orientational ordering observed in experiments, are discussed. The theory developed predicts that chemical disorder marginally affects the nematic/isotropic biphasic coexistence width, but strongly impacts ordering; above a critical chemical disorder threshold orientational ordering is precluded.

The study of sequence heterogeneity effects on phase separation of sequence-disordered liquid crystalline polymers is paramount to modulation of electro-optical properties, piezo and pyro-electricity [1], and also to disclosure of general ordering trends prevalent in proteins with secondary structure [2]. Onsager approach [3], developed for the study of liquid crystals (LC's) with repulsive anisotropic interactions, has been extended and used [4] to analyze single chains and melts of liquid crystalline homopolymers (LCP's). The effect of attractive anisotropic interactions by dipolar coupling was first introduced in the theory of LC's by Mayer and Saupe [5]; their approach was found useful in the study of low molecular weight LC's. LCP's were also studied by lattice models [6], and the Onsager approach was used to correct for lattice artifacts effects in phase behavior [7].

A field theoretic approach to study many chain LCP's was proposed by Gupta and Edwards (GE) [8]; free energy contributions to nematic ordering were computed non-perturbatively, and the Landau expansion method was avoided by summation over all Rouse modes; interaction-wise, both athermal repulsive contributions [3], and the Mayer Saupe dipole-dipole attractive contributions to the inter-segment interaction potentials are present. GE [8] predict that the nematic/isotropic (N/I) transition is first order while the transition temperature is depressed in comparison with low molecular weight rods; their predictions are supported by computer simulations of short nematic chains [11] and by experiments [14]. Recently, GE approach was employed to study orientational ordering in semi-flexible homopolymers embedded in flexible surfaces [12].

Stupp et al. [1], [13] synthesized and characterized by optical microscopy and C13 NMR, orientation and sequence-statistics of thermo-tropic sequence-disordered LCP. In these experiments, optical domains were observed over a broad temperature regime $\sim 120^\circ$; these domains were attributed to a wide biphasic N/I coexistence width, and their occurrence was attributed to sequence-disorder and finite chain length effects. Fredrickson et al. [16], studied via Landau theory the homogeneous chain anisotropy limit of the sequence model [17], and predicted that an increase in chain length diminishes chemical het-

erogeneity effects on the N/I biphasic width.

In order to make closer connection with experiments, in the present work we construct a field theory of LCPs made of stiff mesogens and flexible spacers, randomly distributed on the chain (viz. fig. 1). Sequence-distribution and interaction-wise, our model is an adequate description of the sequence disordered LCPs synthesized in experiments [15]. While the GE method is not applicable here, in the homopolymer limit the present study reproduces the free energy of GE theory [8].

The many-chain Hamiltonian for a solution of sequence disordered LCP's made of mesogenic segments (A's) and flexible segments (B's) is:

$$\begin{aligned}
 H = & \sum_i \int \left(\frac{1 - \theta(n_i)}{2} \frac{3}{2l} \mathbf{u}^2(n_i) + \frac{1 + \theta(n_i)}{2} \frac{\beta \epsilon}{2kT} \dot{\mathbf{u}}^2(n_i) \right) dn_i \\
 & - w \int d\mathbf{r} [\hat{\sigma}^{ii}(\mathbf{r}) \hat{\sigma}^{jj}(\mathbf{r}) - \hat{\sigma}^{ij}(\mathbf{r}) \hat{\sigma}^{ji}(\mathbf{r})] - u \int d\mathbf{r} \hat{\rho}(\mathbf{r})^2 \quad (1) \\
 \rho(\hat{\mathbf{r}}) = & \sum_k \int dn_k \delta(\mathbf{r} - \mathbf{r}(n_k)) \\
 \hat{\sigma}^{ij}(\mathbf{r}) = & \sum_k \int dn_k \frac{1 + \theta(n_k)}{2} \delta(\mathbf{r} - \mathbf{r}(n_k)) \mathbf{u}_k^j(n_k) \mathbf{u}_k^i(n_k) \quad (2)
 \end{aligned}$$

$\mathbf{r}(n_i)$ is the spatial location of the n 'th segment of the i 'th chain, $\mathbf{u}(n_i)$ is the chain tangent of the i 'th chain at n_i and $\theta(n_i)$ is the chemical composition variable of the n_i 'th segment on the i 'th chain. $\theta(n_i) = 1$ for an A segment and $\theta(n_i) = -1$ for a B segment. The sequence heterogeneity, represented by fluctuations in the segment composition along the chain contour obeys a Gaussian process with mean, $\langle \theta \rangle = \frac{2f}{f-1}$, $\delta\theta = \theta(n_i) - \langle \theta \rangle$, and sequence fluctuations $\delta\theta^2 = \langle (\delta\theta(n_i) \delta\theta(n'_j)) \rangle = \delta(n_i - n'_j) 4f(1-f)l$ [18]; f is the fraction of A segments, and l is the statistical segment length.

The first term in eq. 1 is the nearest-neighbors harmonic interaction potential of flexible segments of type B, while the second term in eq. 1 precludes bending of the stiff segments, A's, (viz. line-bounded mesogens, fig. 1). The third term in eq. 1 is the interaction potential of A-A segments by anisotropic (viz. also [8]) alignment of A pairs;

this energetic penalty is zero for aligned tangents of A segments adjacent in space, and w for normal tangents.




Fig. 1: One disordered LCP sequence. Flexible segments are thin and black, mesogen segments are thick and grey

The A-A anisotropic interaction potential, w , contains both athermal and thermo-tropic contributions [8]. The fourth term in eq. 1, is the excluded volume inter-segment interaction. While sequence effects on equi-stiff heteropolymers were treated [16], the present work focuses on the effect of dissimilarity in anisotropy among the stiff mesogens (A) and the flexible spacer (B) on orientational ordering, in lyotropic and thermo-tropic sequence-disordered LCPs.

Below, solution steps are briefly described. First, continuous microscopic orientational tensors are introduced by delta function constraints on the partition function, while the fluctuations of the chain director of the stiff segments is constrained in the usual way (viz. [8] for further details). The partition function at fixed sequence is given by:

$$Z[\theta(n_i), \mathbf{u}(n_i)] = \int \overline{\int} \left[\prod_{n_i, \mathbf{r}} D\mathbf{r}_i(n_i) D\sigma(\mathbf{r}) \right] \exp(-L[\hat{\sigma}(\mathbf{r})]) \prod_{n_i, \mathbf{r}} \delta[\sigma(\mathbf{r}) - \hat{\sigma}(\mathbf{r}) \delta[\mathbf{u}(n_i)^2 \frac{(1 + \theta(n_i))}{2} - 1]] \quad (3)$$

$\hat{\sigma}(\mathbf{r})$ is given in eq. 2; the $\hat{\sigma}(\mathbf{r})$ delta function constraint is expressed with auxiliary fields $\psi^{ij}(\mathbf{r})$, and the disorder average is performed non-perturbatively with the replica trick [20]; replica symmetry breaking (RSB) is not expected and the replica limit is exact; still the disorder average yields a free energy functional non-local in polymer modes, and the GE approach [8] cannot be used.

The partition function in eq. 3 may be also viewed as the path integral for a quantum Green function in imaginary time Lagrangian representation. For compu-

tational convenience, we exchange the Lagrangian to a Hamiltonian representation [21], and the free energy is computed variationally in the Hamiltonian reference frame:

$$H_\alpha = \sum_\alpha \left(-\frac{1}{4A} \hat{\mathbf{p}}_\alpha^2 + h_\alpha \hat{\mathbf{u}}_\alpha^2 \right) \\ h_\alpha = \frac{3(1 - \bar{\theta})}{4l} + \frac{(1 + \bar{\theta})(\lambda + \psi_\alpha)}{2}; A = \frac{\beta\epsilon(1 + \bar{\theta})}{4} \quad (4)$$

$\hat{\mathbf{p}}_\alpha^2$ and $\hat{\mathbf{u}}_\alpha^2$ are the α quantum kinetic energy and coordinate operator in imaginary time with $\alpha = x, y, z$. ψ_α is the principal axis representation of the fields $\sqrt{-1}\psi^{ij}$ while λ equals $\sqrt{-1}$ times the auxiliary field that sets the magnitude of $\mathbf{u}(n_i)$ to 1 for the A segments in eq. 3. Based on eq. 4, creation/annihilation operators, (a^+, a) , are introduced to facilitate computation of orientational averages in the free energy.

$$\hat{\mathbf{u}}_\alpha = \frac{a_\alpha + a_\alpha^+}{\sqrt{2m\omega_\alpha}}; \hat{\mathbf{p}}_\alpha = (a_\alpha + a_\alpha^+) \frac{\sqrt{m\omega_\alpha}}{2} \\ m = 2A; \omega_\alpha = \left(\frac{h_\alpha}{A}\right)^{\frac{1}{2}}; [a_\alpha, a_\beta^+] = \delta_{\alpha,\beta} \quad (5)$$

Omitting presentation of the intermediate calculation [22], the free energy per segment obtained is:

$$F = \frac{1}{2} \sum_\alpha \left(\frac{h_\alpha}{A} \right)^{\frac{1}{2}} + \frac{\bar{\delta}\theta^2 3}{64A^3} \sum_\alpha h_\alpha + \frac{\bar{\delta}\theta^2 C}{32A^2} \sum_\alpha S_\alpha \\ - \frac{\bar{\delta}\theta^2}{64A} \sum_\alpha \frac{S_\alpha^2}{h_\alpha} - \lambda k + \frac{1}{\rho} \left(\frac{w}{2} \left[\left(\sum_\alpha \sigma_\alpha \right)^2 - \sum_\alpha \sigma_\alpha^2 \right] - \sum_\alpha \psi_\alpha \sigma_\alpha \right) \quad (6)$$

$$S_\alpha = -\frac{3}{2l} + \psi_\alpha + \lambda; C = \frac{\beta\epsilon}{2}; k = \frac{(1 + \bar{\theta})}{2} \quad (7)$$

ρ is the segment density; σ_α is $\sigma_{i,j}$ in principal axis representation:

$$\sigma^\alpha = \begin{pmatrix} a - b & 0 & 0 \\ 0 & a + b & 0 \\ 0 & 0 & 2a \end{pmatrix} \quad (8)$$

For uniaxial ordering the orientational order parameter, $\langle S \rangle$, is given by $\langle S \rangle = \frac{-3a}{b}$. $1 > \langle S \rangle > 0$ signals uniaxial nematic ordering while $-0.5 < \langle S \rangle < 0$ signals discotic ordering. In Einstein notation, in the isotropic phase, $\sigma^{ii}(\mathbf{r}) = \rho_A(\mathbf{r})$, otherwise, $\sigma^{ii}(\mathbf{r}) \neq \rho_A(\mathbf{r})$. The homopolymer limit of the free energy, i.e. $f=1$ in eq. 6, reproduces exactly the GE free energy of

a many-chains LCPs (viz. eq. 32 in [8]), and the minimal value for uniaxial ordering, $\langle S \rangle = 0.25$, obtained analytically in [8]), is reproduced herein.




Fig. 2: Numerical results for uniaxial ordering $\langle S \rangle$ (solid lines) and chemical potential per segment (long dashed lines) variation with segment density, ρ . Comparison among the thermodynamical stable phase (thick line) and the unstable phase (thin line); $f=0.938$, $w=10$, $\beta e=5$, $l=8$.

Now, the free energy given in eq. 6 is minimized analytically by the fields $\sigma_\alpha, \psi_\alpha, \lambda$ with $\alpha = x, y, z$; seven non-linear self-consistent equations are obtained and solved numerically by direct iteration with proper mixing of coefficients [9]; more computational and analytical details will be given elsewhere [22]. Fig. 2. depicts numerical results for lyotropic stability of disordered LCP at small disorders. Thick lines in fig. 2 are uniaxial ordering curves for $\langle S \rangle$ while dotted lines are the chemical potentials of the stable phases.




Fig. 3: Numerical results for uniaxial ordering $\langle S \rangle$ variation with segment density, ρ and composition, f ; $w=10$, $\beta e=5$, $l=8$; f values follow upper to lower $\langle S \rangle$ curves; $f=0.98, 0.94, 0.93, 0.88$.

at a finite density depicts a first order N/I transition; fig. 2 depicts also another stable solution for $\langle S \rangle$ (viz. other thick line); this solution increases continuously with increase in density from $\langle S \rangle = 0$, i.e. a second or higher order N/I transition.

The first order line bears a lower chemical potential at all densities studied (viz. thick dashed line), and describes the physical ordering scenario that should be observed in simulation or experiments. The weak N/I transition, is also numerically stable, but has a higher chemical potential (viz. thin dashed line) and it should not be observed.

Fig 3. is a numerical study of sequence heterogeneity effects on lyotropic nematic ordering. Only stable solutions with lowest chemical potentials are plotted. Fig. 3 depicts $\langle S \rangle$ - the nematic order parameter variation with density for decreasing fractions of the stiff segments, f . The entropy carried by the flexible runs have dramatic effects on ordering; Fig. 3 shows that a relatively small increase in the average number of flexible segments decreases notably the overall uniaxial ordering, and shifts the segment density at the N/I threshold to higher values. Interestingly, while the presence of sequence heterogeneity impacts strongly the value of the segment-density-N/I-threshold, the presence of disorder carried by the fluid does not change the order of the N/I transition, and the transition remains first order.




Fig. 4: Numerical results for N/I biphasic width variation with fraction of mesogen segments, f ; $w=10$, $\beta e=5$, $l=8$.

Recently Radzihovsky et. al. [23] have shown that weak external disorder is sufficient to destabilize the nematic phase in LC rods; in the present system, wherein the disorder is carried by the fluid, nematic ordering is also affected; our calculation show that above a critical value of disorder strength, the nematic ordering is destroyed and the phase becomes isotropic, yet the overall effect on uniaxial ordering is less pronounced than the effect of external disorder.

A Maxwell construction is employed (viz. [8]) for the

calculation of the N/I coexistence region. Free energies and chemical potentials in the vicinity of the N/I transition are computed numerically for the isotropic and the nematic phases for several fractions of mesogenic segments. Δ , the N/I coexistence width is given by $\Delta = \rho_i - \rho_n$; ρ_i is the segment density in the isotropic phase while ρ_n is the segment density in the nematic phase at coexistence. Fig. 4 is a study of sequence heterogeneity effects on the N/I coexistence. In fig. 4 numerical results for the coexistence width dependence on mesogenic fraction are depicted. Larger sequence heterogeneities increase the N/I coexistence width almost 3 folds that of a semi-flexible homopolymer.




Fig. 5: N/I phase diagram in f and ρ variables; $w=10$, $\beta e=5$, $l=8$; squares are (f, ρ_i) points, circles are (f, ρ_n) points.

Fig. 5 depicts the effect of sequence heterogeneity on orientational ordering. The entropy carried by mesophases rich in flexible segments destroys the nematic ordering below a specific fraction of mesogen segments (which is density dependent), the nematic phase loses stability, while the isotropic phase remains stable. For the values of parameters in fig. 5 at melt densities, ($\rho = 1$), the critical fraction of mesogen segments, f , is $f_c = 0.76$. The N/I coexistence width displayed in fig. 5 as the horizontal distance among an adjacent square (ρ_i) and circle (ρ_n) is marginal at all densities displayed.

Invoking the homogeneous isotropic limit, (i.e. the difference in anisotropy of A and B segments is negligible) the sequence heterogeneity effects vanish in the infinite chain limit in agreement with [16]; In many experimental scenarios, (i.e. $(MBPE - (methylene)_y)$ with $y=17, 18, 20$ [10]) one segment is stiff, the other is flexible and rigorous treatment of anisotropy dissimilarity of A and B segments developed herein is crucial. In the present work, we showed that for long chains, $\frac{\beta e}{2}/L \ll 1$, the sequence heterogeneity effect on the N/I biphasic region does not vanish, but in most cases is small with a $\Delta T \sim 10^\circ$.

contribution to the N/I biphasic width. Our predictions suggest that optical mesophases in the regime $\frac{\beta e}{2}/L \ll 1$ cannot be associated with a wide N/I biphasic regime induced by sequence-heterogeneity, and a different explanation of experiments, based on a rigorous account of the optical scale ordering of mesophases (e.g. $\sigma(\mathbf{k}) \neq 0$), is necessary. The occurrence of optical domains observed in experiments, [15], can also be a signature of slow ordering dynamics during a finite heating/cooling rate process. Currently, we are studying both scenarios.

Acknowledgment We gratefully acknowledge Harvard University for financial support.

- [1] J. S. Moore and S. I. Stupp *Macromolecules*, **20**, 273, (1987)
- [2] T. E. Creighton *Proteins, Structure and Molecular Properties*, W. H. Freeman and Company, (1993)
- [3] L. Onsager *Ann. N. Y. Acad. Sci.*, **51a**, 627, (1949)
- [4] A. Yu Grosberg and A. R. Khokhlov *Sov. Sci. Rev. A. Phys.*, **8**, 147, (1987)
- [5] W. Maier and A. Z. Saupe *Naturforsch.*, **12**, 882, (1959)
- [6] P. J. Flory, *Proc. Roy. Soc.* **234**, 73, (1956)
- [7] P. J. Flory and G. Ronca *Mol. Cryst. Liq. Cryst.*, **54**, 289, (1979)
- [8] A. M. Gupta and S. F. Edwards *J. Chem. Phys.*, **98**, 1588, (1993)
- [9] B. Carnahan, H. A. Luther and J. O. Wilkes *Applied Numerical Methods* (Wiley, New York), (1969)
- [10] V. Percec and Y. Tsuda *Macromolecules*, **23**, 3509, (1990)
- [11] M. Dijkstra and D. Frenkel *Phys. Rev. E*, **51**, 5891, (1995)
- [12] R. Podgornick *Phys. Rev. E.*, **54**, 5268, (1996) ; *ibid Phys. Rev. E.*, **52**, 5170, (1995)
- [13] P. G. Martin and S. I. Stupp *Macromolecules*, **21**, 1222, (1988); *ibid* **21**, 1288, (1988)
- [14] J. F. Allest, P. Maissa, A. ten Bosch, P. Sixou, A. Blumstein, R. Blumstein, J. Teixeira, and L. Noirez *Phys. Rev. Lett.*, **61**, 2562, (1988)
- [15] S. I. Stupp, J. S. Moore, and P. G. Martin *Macromolecules*, **21**, 1228, (1988)
- [16] G. H. Fredrickson and L. Leibler *Macromolecules*, **23**, 531, (1990)
- [17] E. I. Shakhnovich and A. M. Gutin *J. Physique*, **50**, 1843, (1989)
- [18] L. Gutman and A. K. Chakraborty *J. Chem. Phys.*, **101**, 10074, (1994); **103**, 10733, (1995)
- [19] K. F. Freed *Advanced in Chemical Physics*, **22**, 1, (1972)
- [20] K. Binder and A. P. Young *Rev. Mod. Phys.*, **58**, 801, (1986)
- [21] M. Swanson *Path Integrals and Quantum Processes*, Academic Press, INC, Harcourt Brace Jovanovich, Publishers, (1992)
- [22] L. Gutman and E. I. Shakhnovich *J. Chem. Phys.*, in preparation
- [23] L. Radzihovsky, and J. Toner *Phys. Rev. Lett.*, **79**, 4214, (1997)